

SHAHABAD CREAM

Pale off-white. Interior flooring line.

The palest bed worked at Miriyan. Shahabad Cream is a fine, close-grained off-white with faint warm veining and very low mineral speckle. It calibrates and polishes cleanly, which is why it is sold almost entirely as interior floor and wall tile.

TECHNICAL DATA

PROPERTY	VALUE	TEST STANDARD
Compressive strength, dry	98 MPa	BS EN 1926
Compressive strength, saturated	83 MPa	BS EN 1926
Flexural strength	13.9 MPa	BS EN 12372
Water absorption	0.61 %	BS EN 13755
Apparent density	2,540 kg/m³	BS EN 1936
Abrasion resistance	20.8 mm	BS EN 14157
Slip resistance, dry	72 PTV	BS 7976-2 pendulum
Slip resistance, wet	34 PTV	BS 7976-2 pendulum
Frost resistance	Pass, 48 cycles, < 1.2 % loss	BS EN 12371
Open porosity	1.7 %	BS EN 1936
Thermal shock	No visible change, 20 cycles	BS EN 14066

FINISHES

FINISH	NOTES
Honed 220 grit	Standard interior floor finish
Polished	Lobby and wall applications, low traffic
Brushed	Softened matt, hides traffic marking
Shot blasted	Wet rooms and thresholds

SHAHABAD CREAM

Sizes, applications and packing specification

SIZES AND THICKNESSES

SIZE	THICKNESS	FINISH	TOLERANCE
300 × 300 mm	16 / 20 mm	Honed, polished	± 0.8 mm
600 × 300 mm	16 / 20 mm	Honed, polished, brushed	± 0.8 mm
600 × 600 mm	20 mm	All finishes	± 1.0 mm
900 × 600 mm	20 mm	Honed	± 1.5 mm
Skirting 600 × 100 mm	16 mm	Honed, polished	± 0.8 mm

APPLICATIONS

APPLICATION	POSITION
Paving	On request
Cladding	Suitable
Flooring	Recommended
Kerbs	On request
Interior	Recommended

Not recommended for external paving in exposed UK conditions. Where an external application is required, specify 30 mm shot blasted and a sheltered location, and confirm with our technical team first.

PACKING SPECIFICATION

ITEM	SPECIFICATION
Crate	Heat-treated timber, ISPM 15 stamped, 1180 × 780 × 950 mm
Contents per crate	38 m² at 16 mm / 30 m² at 20 mm
Gross crate weight	1,690 kg gross at 20 mm
Crates per 20 ft	16
Area per 20 ft	505 m² at 20 mm
Supply allowance	Supply allowance 3 % on calibrated tile

Quotations are issued to your nearest port or delivered to your yard, on request. Values shown are batch-test results from the Miriyan processing unit, verified annually on UK-landed samples. Certificates are issued per shipment and reference the crate marks.